

APPENDIX

--ABSTRACT OF THE DISCLOSURE

An object of the present invention is to provide a high strength Mg based alloy and a Mg based casting alloy having a good fluidity and a good mechanical property, and a molded article using the alloy. A high strength Mg based alloy, which contains, by weight, 12 to 20% of Al, 0.1 to 10% of Zn; 0.1 to 15% of Sn; and 0.05 to 1.5% of Mn.--